

Test data provided by raw material manufacturer or an ISO 17025 registered 3rd party lab.  
Original test data is stored in the Darcoïd Compound Database



6/14/2022

Darcoïd Compound: 5033

## COMPOUND DATA SHEET

VMQ, 45±5 Shore A

This compound will meet or exceed the specifications listed and has the following physical properties:

ORIGINAL PROPERTIES	TEST METHOD	SPEC.	RESULTS
Hardness, Shore A	D-2240	45	46
Tensile Strength, MPa, min	D-412	6	8.4
Elongation, % min	D-412	400	462

950 3<sup>rd</sup> Street | Oakland, California 94607 | (800) 632-7264

This document is the confidential property of Darcoïd and is not to be shared with any companies or persons outside of the nondisclosure agreement without the written permission from Darcoïd.

